



## NIPPELUX TROPICAL ANTI-FOULING

<b>TYPE</b>	A classical anti-fouling paint with a high percentage of cuprous oxide.
<b>USES</b>	Protection against marine growth on ship bottoms.
<b>SPECIAL FEATURES</b>	Offers efficient and lasting protection against marine growth on ship bottoms.
<b>TEXTURE</b>	Semi-gloss.
<b>SURFACE DRY</b>	1 hour at 20°C or 40 minutes at 30°C.
<b>HARD DRY</b>	10 hours at 20°C or 6 hours at 30°C.
<b>OVERCOATING INTERVAL</b>	16 hours at 20°C or 12 hours at 30°C.
<b>IMMERSION IN WATER</b>	16 hours at 20°C or 12 hours at 30°C.
<b>NON-VOLATILE CONTENT</b>	60.0% by volume.
<b>FILM THICKNESS - WET</b>	85 microns.
<b>FILM THICKNESS - DRY</b>	50 microns.
<b>THEORETICAL COVERAGE</b>	12.0 sq. metres per litre.
<b>PRACTICAL COVERAGE</b>	9.6 sq. metres per litre (loss factor 20%).
<b>SPECIFIC GRAVITY</b>	1.54 kg per litre.
<b>THINNER</b>	1901 Nippelux Thinner.
<b>FLASH POINT</b>	32°C.
<b>COLOUR</b>	Red Brown.
<b>STANDARD PACKING</b>	5 litres and 20 litres.
<b>SURFACE PREPARATION</b>	The surface must be clean and dry, free from grease and oil.
<b>PAINT PREPARATION</b>	Ready for use after thorough stirring.
<b>APPLICATION – AIRLESS SPRAY</b>	Delivery Pressure: 140-170 kg/cm <sup>2</sup> . Tip Size: 0.017" at 60° angle. 0.019" at 60° or 70° angle. Dilution: 0-5%. Film Thickness – Wet: 85 microns per coat Dry: 50 microns per coat.
<b>APPLICATION – BRUSH OR ROLLER</b>	Dilution: 0-5%.
<b>PRECAUTIONS</b>	It contains volatile and inflammable solvents. Ensure adequate ventilation during use, avoiding naked flame, welding operations and other fires. Avoid contact with skin.
<b>NOTE</b>	Values given are average for reference. Actual values may vary, depending on conditions.